



# PREMIUM AUTOMOTIVE PERFORMANCE SPECIFICATIONS

## QDP CERAMIC FILMS

Type of Films	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	TSER	NB
QDP Ceramic Charcoal 05	2.0 Mil	4%	6%	11%	6%	83%	<1%	96%	0.39	66%	76%
QDP Ceramic Charcoal 20	2.0 Mil	18%	6%	16%	6%	78%	<1%	82%	0.40	62%	76%
QDP Ceramic Charcoal 30	2.0 Mil	31%	7%	23%	6%	71%	<1%	65%	0.49	58%	76%
QDP Ceramic Charcoal 38	2.0 Mil	38%	7%	25%	6%	69%	<1%	58%	0.51	56%	76%
QDP Ceramic Charcoal 42	2.0 Mil	42%	7%	28%	6%	66%	<1%	54%	0.54	53%	76%
QDP Ceramic Charcoal 46	2.0 Mil	46%	7%	30%	6%	64%	<1%	49%	0.55	52%	76%
QDP Ceramic Charcoal 50	2.0 Mil	51%	7%	32%	6%	62%	<1%	44%	0.56	51%	76%

## ICE COOL FILMS

Type of Films	T	VLT	VLR	SET	SER	SEA	UVT	GR	SC	TSER	NB
ICE Cool Grey 40	2.0 Mil	38%	6%	21%	6%	73%	<1%	59	0.48	58	92%
ICE Cool Grey 50	2.0 Mil	53%	7%	29%	6%	65	<1%	42	0.55	53	92%
ICE Cool Grey 70	2.0 Mil	69%	8%	35%	7%	58	<1%	24	0.59	49	90%
ICE Cool Grey 80	2.0 Mil	79%	9%	47%	7%	46	<1%	13	0.69	40	76%



[WWW.QDPNOW.COM](http://WWW.QDPNOW.COM)

**T** : Thickness **VLT** : Visible Light Transmittance **VLR** : Visible Light Reflectance **SET** : Solar Energy Transmittance  
**SER** : Solar Energy Reflectance **SEA** : Solar Energy Absorbance **UVT** : Ultra Violet Transmittance **GR** : Glare Reduction  
**SC** : Shading Coefficient **TSER** : Total Solar Energy Rejection **NB** : NIR Blocking AT 1025 NM

Global Window Films are available through Global Dragon in the following States: Alabama, Arkansas, Illinois, Iowa, Michigan, Mississippi and North Carolina!